

TECHNICAL DATA SHEET 5246

Atlantic Resin No.5246

Atlantic Epoxy Clear Coating & Casting Resin No. 5246 is a fast curing epoxy resin specially designed for use in applications requiring a strong, durable coating where low colour and high UV resistance is required. 5246 has excellent water resistance, chemical resistance, mechanical properties and excellent adhesion to a variety of substrates.

Special Features:

Fast cure

Low viscosity, easy to apply

Low tendency to yellow on exposure to UV

Excellent mechanical properties

Excellent chemical and water resistance

Excellent adhesion

Mix Ratio

RESIN EP5246 : HARDENER H5246

By Weight 100 : 50

Product Data

Property	Units	EP 5246	H5246	Mix
Material	-	Epoxy Resin	Formulated Amine	-
Appearance	-	Colourless liquid	Colourless liquid	Colourless liquid
Viscosity (25°C)	mPa.s	8000 – 11000	370 – 570	2200 – 2600
Density (25°C)	g/cm ³	1.15 – 1.20	0.99 – 1.04	1.09 – 1.14

Curing Data

Property	Units	Typical Value
Pot life (200g, 25°C)	Minutes	30 – 50
Cure Time (200g, 25°C)	Hours	24
Full Cure (25°C)	Days	7
Minimum Curing Temperature*	°C	15
Recommend Casting Thickness*	mm	2 – 5

*See "Cure & Post Cure" section.

Cured Properties

Properties	Standard	Units	Result (Post Cure)
Hardness	BS EN ISO 868	Shore D	85 – 90
Tensile Strength	BS EN ISO 527	MPa	59.0 – 64.0
Elongation at Break	BS EN ISO 527	%	4.0 – 6.0
Tensile Modulus	BS EN ISO 527	MPa	1600 – 1900
Flexural Strength	BS EN ISO 178	MPa	77.0 – 83.0
Flexural Modulus	BS EN ISO 178	MPa	2400 – 2700
Glass Transition Temperature (Tg)	DMA	°C	60 – 65

Method of Use

Preparation

Prior to use, ensure that the resin is compatible with the substrates, reinforcements or fillers being used. Inspect both components for any signs of crystallization.

Crystallization can cause the liquid to become cloudy or viscous, and in extreme cases, the product could become solid. If either component has crystallized, heat to 40°C using sufficient extraction to remove any fumes.

Shake the containers periodically until the product becomes a clear liquid. Allow the product to cool to room temperature before use.

Do not apply resin if the ambient or substrate temperature is less than minimum curing temperature, see “Curing Data” section.

Mixing and Application

Thoroughly mix the resin and the hardener according to the indicated mixing ratio, avoiding air entrapment and make certain that the material at the bottom and sides of the container is well stirred into the centre. Vacuuming the mixed material will help produce a void free cured material. The two components should be mixed and applied within the pot life.

Cure and Post Cure

The system is designed to be used and cured at room temperature. Lower ambient temperatures will result in slower cure. The product should always be processed and cured at temperatures above the minimum curing temperature, see “Curing Data” section.

Incomplete cure could occur if cast in thin section. Exact cure time will depend on the size and geometry of the casting and should be determined by customer testing. Thinner castings will take longer to cure than thicker castings, but generally, the product can be demoulded after 24 hours at 25°C.

Incomplete cure can result in slight distortions or deformations of the components if forces are applied. The recommended casting thicknesses stated above may not apply to small or large volume castings.

Thicker castings will tend to shrink more than thinner castings due to the amount of heat generated.

It is not necessary, but if desired, a step wise post cure treatment can be used to maximise cured properties. Allow the product to cure at room temperature for at least 24 hours, then heat to 40°C for 1 hour, followed by 60°C for 1 hour, followed by 80°C for 3 hours.

To prevent any distortion during the post cure cycle, the part should be placed on a conformer. When post-curing is complete, let the unit cool down slowly to room temperature, preferably in the oven. Sudden change in temperature can cause distortion or warping.

Storage

5246 and HARDENER H5246 should be stored in original, unopened containers between 15 and 25°C. If stored at lower temperatures for prolonged periods of time, 5246 can crystallize, see “Preparation” section for more details. If stored under the above conditions, 5246 and HARDENER H5246 will have a shelf life of 12 months.

Packaging

EP 5246 is supplied in 250g, 2kg, 4kg and 25kg containers.

HARDENER H5246 is supplied in 125g, 1kg, 2kg and 12.5kg containers.

Further Information

This data is not to be used for specifications. Values listed are for typical properties and should not be considered minimum or maximum.

This technical advice, whether verbal, or in writing is given in good faith, but without warranty – this also applies where proprietary rights of third parties are involved. It does not release you from the obligation to test the products supplied as to their suitability for the intended process and use.

Before using the products, users should familiarise themselves with the relevant Technical and MSDS provided.

SWA Art Studios.

Unit 1a Cligga Head Ind Est, St Georges Hill, Perranporth, Cornwall, TR6 0EB